

RT152



Low Viscosity Clear Epoxy Resin System

Description

RT152 is an optically clear, very low viscosity epoxy resin system.

Benefits

- Water white and optically clear
- Has a 4-8 hour working life after mixing depending on mass
- High surface energy and readily wets and wicks between surfaces
- Low viscosity - reduces air entrapment
- Good impact and thermal shock resistance
- Available in easy-to-use TwinPacks or bulk

Typical Properties

Curing

Work life at 23°C (<25g): 4 hours
Work life at 23°C (<4g): 8 hours

Cure time for mass <100g to control exotherm

Cure time at 23°C: 48 hours
Cure time at 80°C: 90 minutes

Typical Performance (measurements at 23°C)

Mixed viscosity: 0.5-1.0 Pa s
Density: 1.05
Shore Hardness: 82 D
Operating Temperature: -60°C to 200°C
Optical transmission: >97%

Colour

Clear

Related Products

- RT151 low viscosity epoxy resin system
- The Resintech potting and fibre optic adhesive range

Issue 2 - April 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

Resintech Limited

Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom

t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk