

RT154TH



Thixotropic Thermally Resistant Epoxy Adhesive

Description

RT154TH provides outstanding thermal resistance and low shrinkage in fibre optic applications.

Benefits

- Will withstand high temperature steam autoclaving and operate for short periods at 350°C
- Excellent adhesion to glass fibres as well as metals, ceramics and many plastics
- Outstanding impact and thermal shock resistance
- Can be gelled prior to full cure
- Low shrinkage on cure, reducing internal stresses in multiple fibre assemblies
- Excellent sealing with very high moisture and chemical resistance, and low outgassing
- Very long work life after mixing
- Supplied in DuoSyringe for easy application
- Standard size is 50ml, with associated mixing nozzles and dispenser guns

Typical Properties

Mix ratio:	100 parts hardener to 100 parts resin
Mixed viscosity:	15 Pa.s (15000 cPs)
Work life:	12 hours @ 23°C (4g in syringe)
Curing Schedule:	Gel @ 80°C for 2 hours (optional) 135°C for 30 minutes 150°C for 15 minutes

Optimum Properties (cured for 15 minutes @ 150°C)

Glass Transition:	> 150°C
Density:	1.25
Hardness:	92 D
Modulus:	2 Gpa
Operating Temperature:	- 60 to 250°C
Shrinkage on Cure	< 3.5%
Thermal Expansion	55 x 10 ⁻⁶ cm/cm/°C

Related Products

- RT154 (Unfilled, low viscosity version of RT154TH)
- The Resintech fibre optic adhesive range, including RT153FC high temperature adhesive

Issue 6 - March 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

Resintech Limited

Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom

t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk