

RT156



Medium Temperature Curing Epoxy Adhesive

Description

RT156 is excellent for bonding and potting fibre optic components, using moderate cure temperatures.

Benefits

- Acceptable cure speed at 75°C
- High surface energy and low viscosity. Readily wets and wicks between optical fibres
- Excellent adhesion to glass fibres as well as metals, ceramics and many plastics
- Good impact and thermal shock resistance
- Excellent moisture and chemical resistance
- Low heat build up on cure gives lower stresses
- Standard colour is blue. Clear and other colours available to special order
- Available in 2g and 4g TwinPack sachets as well as various bulk sizes

Typical Properties

Mix ratio:	25 parts hardener to 100 parts resin
Mixed viscosity:	0.5 – 1.5 Pa.s (500 – 1500 cPs)
Work life:	2 hours @ 23°C (4g in syringe)
Surface Tension:	42 - 44 mN/m
Curing Schedule:	25°C for 24 hours 75°C for 20 minutes 100°C for 5 minutes

Optimum Properties (cured for 5 minutes @ 100°C)

Glass Transition	105°C
Thermal Expansion	55 x 10 ⁻⁶ cm/cm/°C
Refractive Index:	1.55
Density:	1.10
Hardness:	85 D
Operating Temperature:	-60 to 200°C
Lap Shear – Al/Al	11 MPa (@ 23°C)

Related Products

- The Resintech fibre optic adhesive range, including RT153FC high temperature adhesive

Issue 8 - March 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

Resintech Limited

Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom

t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk