

Technical Data

RT157

Optical Clear Fast Curing Epoxy Adhesive

Description

RT157 is excellent for bonding and potting optical components, where clarity is important.

Benefits

- Sets in minutes at room temperature
- Reaches handling strength in 30 minutes
- Optically clear
- High surface energy. Readily wets and wicks between fibres
- Good adhesion to glass fibres as well as metals, ceramics and many plastics
- Good impact and thermal shock resistance
- Excellent for bonding and potting optical components such as prisms, LED's and fibres
- Available in 50g Duosyringe system

Typical Properties

Work life:	5 minutes at 23°C (2g)
Cure Time vs. Temperature:	2 hours at 23°C 10 minutes at 65°C

Optimum Properties (cured for 24 hours at 23°C)

Thermal Expansion	55×10^{-6} cm/cm/°C
Shrinkage on Cure	3%
Density:	1.20
Hardness:	70 D
Refractive Index	1.54
Operating Temperature:	-60 to 125°C
Lap Shear – Al/Al	8 MPa (at 23°C)

Colour

Clear

Related Products

- The Resintech fibre optic adhesive range, including RT153F high temperature adhesive

Resintech Limited warrants only that it's products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for it's intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.