

# RT183



## Electrically Conductive Epoxy Adhesive

### Description

RT183 is specifically designed for shield and connector termination in EMC applications.

### Benefits

- Easy to use medium viscosity adhesive
- Room temperature or elevated temperature cure
- Easy to apply using the Resintech DuoSyringe system
- Standard size is 25ml (50g), with associated mixing nozzles and dispenser guns

### Typical Properties

#### Curing

Work life at 23°C:	60 minutes
Time to handling at 23°C:	8 hours
Cure time at 23°C:	24 hours
Cure time at 80°C:	1 hour
Cure time at 100°C:	30 minutes

#### Typical Performance (cured for 30 minutes at 100°C)

Lap Shear (Al / Al @ 23°C)	8 MPa
Resistivity (@ 23°C)	<10 <sup>-2</sup> ohm-cm
Lap Shear (Al / Al, after 172hrs @ 150°C)	8 MPa
Resistivity (after 172hrs @ 150°C)	<0.01 ohm-cm
Lap Shear (Al / Al, after 172hrs @ 40°C in water)	6 MPa
Resistivity (after 172hrs @ 40°C in water)	<0.01 ohm-cm
Operating temperature range	-55°C to 150°C

### Colour

Silver

### Related Products

- The ShieldFast® Range
- RT125 flexible high performance epoxy adhesive

Issue 7 - April 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

**Resintech Limited**

**Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom**

**t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk**