

RT323



High Temperature Epoxy Resin System

Description

RT323 is a clear low viscosity epoxy resin system with excellent high temperature performance.

Benefits

- Long pot life for ease of use
- Low viscosity giving excellent potting of intricate components
- Good handling characteristics with low dermatitic response
- High speed cure at elevated temperatures
- Outstanding temperature and chemical resistance
- Available in easy-to-use TwinPacks or bulk

Typical Properties

Curing (15g mass)

Work life at 23°C:	4 hours
Cure time at 60°C:	180 minutes
Cure time at 80°C:	30 minutes
Cure time at 100°C:	10 minutes
Cure time at 120°C:	4 minutes

Typical Performance (measurements at 23°C)

Mixed viscosity (at 23°C):	2 Pa s
Density (at 23°C):	1.15
Shore Hardness:	85 D
Glass Transition:	140°C
Operating Temperature:	-50°C to 200°C
Solvent Resistance:	Excellent
Lap Shear (Al/Al at 23°C):	11 MPa

Colour

Clear

Related Products

- The Resintech range of potting epoxies

Issue 5 - April 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

Resintech Limited

Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom

t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk