

# RT350



## Low Viscosity Highly Flexible Epoxy Resin System

### Description

RT350 is an unfilled low viscosity epoxy resin system that will cure in thick sections at room temperature.

### Benefits

- Unfilled low viscosity system
- Excellent potting and encapsulation system with good flow properties
- Good temperature and oil resistance
- Rapid curing system leading to handling within 60 minutes
- High level of adhesion and peel values to flexible materials
- Low level of exotherm during cure and is therefore safe to use on delicate components
- Available in easy-to-use TwinPacks

### Typical Properties

#### Curing (50g mass)

Work life at 23°C:	40 minutes
Cure time at 23°C:	8 hours

#### Typical Performance (measurements at 23°C)

Mixed viscosity:	<5 Pa s
Density:	1.15
Tensile Strength:	20 Mpa
Electric Strength:	13 Kv/mm
Volume Resistivity:	10 <sup>14</sup> ohm/m
Permittivity:	<5
Operating Temperature:	-40°C to 150°C

### Colour

Black

### Related Products

- The Resintech range of potting epoxies

Issue 5 - April 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

**Resintech Limited**

**Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom**

**t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk**